

HEART

MADE IN JAPAN	GLAZED PORCELAIN
---------------	------------------

PACKAGING

COLOR CODE	SIZE	BOX			PLT		
2C/3C/4D/5D/ 10C/11B/20A/ 20B/25E MIX1/2/3/4	SHEET SIZE	SH	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
	12"x12" (299x301mm)	35	33.95	41.8	45	1527.75	1,881
	PIECE SIZE	SH	SQ.M.	KG(NET WEIGHT)	BOX	SQ.M.	KG(NET WEIGHT)
	1"x1" (23x23x4mm)	35	3.12	19	45	140.40	855

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.72% on average.	JIS A 1509-3 : 2008
Crazing Resistance	No Crazing.	JIS A 1509-8 : 2008
Frost Resistance	No deterioration.	JIS A 1509-9 : 2008
Chemical Resistance	As below:	JIS A 1509-10 : 2008
Ammonium chloride solution	No change.	
Hydrochloric acid solution	No change.	
Citric acid solution	No change.	
Potassium hydroxide solution	No change.	
Sodium hypochlorite solution	No change.	

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: $\pm 0.8\text{mm}$ (22.2 ~ 23.8mm)

Clean with neutral detergent.



MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>