

OHM

MADE IN JAPAN	GLAZED PORCELAIN
---------------	------------------

PACKAGING

COLOR CODE	SIZE	BOX			PLT		
		PC	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
OHM-1/2/3/4/5/6	4"x8" (97x197x9-11mm)	60	12.60	52.8	40	504.00	2,112
		PC	SQ.M.	KG(NET WEIGHT)	BOX	SQ.M.	KG(NET WEIGHT)
		60	1.14	24	40	45.60	960

*SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.02% on average.	JIS A 1509-3 : 2014
Crazing Resistance	No Crazing.	JIS A 1509-8 : 2014
Frost Resistance	No deterioration.	JIS A 1509-9 : 2014
Bending Fracture Load	2559.14N on average	JIS A 1509-4 : 2014
Bending Strength	56.48 N/mm ² on average	JIS A 1509-4 : 2014
Chemical Resistance	As below:	JIS A 1509-10 : 2020
Ammonium chloride solution	No change.	
Hydrochloric acid solution	No change.	
Citric acid solution	No change.	
Potassium hydroxide solution	No change.	
Sodium hypochlorite solution	No change.	

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: $\pm 1.2\text{mm}$ / $\pm 2.0\text{mm}$ (95.8 ~ 98.2mm / 195 ~ 199mm)

Clean with neutral detergent.

3mm joint is recommended.

**MARUMAN SHOKAI CO., LTD.**

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>