ZELDA

| MADE IN JAPAN | | | GLAZED PORCELAIN | | | | | |
|---------------------|------|-----|------------------|-----|--|--|--|--|
| PACKAGING PACKAGING | | | | | | | | |
| COLOR CORE | CIZE | вох | | PLT | | | | |

| COLOR CODE | SIZE | вох | | PLT | | | |
|-------------------------|---------------------------------|-----|--------|----------------|-----|--------|----------------|
| | | PC | SQ.FT. | LB(NET WEIGHT) | BOX | SQ.FT. | LB(NET WEIGHT) |
| ZLD-100/200/ 300/400 | 5-3/4"x5-3/4" (145x145x11mm) | 60 | 13.80 | 50.6 | 40 | 552.00 | 2,024 |
| | | PC | SQ.M. | KG(NET WEIGHT) | вох | SQ.M. | KG(NET WEIGHT) |
| | | 60 | 1.26 | 23 | 40 | 50.42 | 920 |

^{*}SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

| Test | Result | Specification | | |
|------------------------------|------------------------------------|----------------------|--|--|
| Water Absorption | 0.02% on average. | JIS A 1509-3 : 2014 | | |
| Crazing Resistance | No Crazing. | JIS A 1509-8 : 2014 | | |
| Frost Resistance | No deterioration. | JIS A 1509-9 : 2014 | | |
| Bending Fracture Load | 2,225.36N on average | JIS A 1509-4 : 2014 | | |
| Bending Strength | 71.36N/mm2 on average | JIS A 1509-4 : 2014 | | |
| nemical Resistance As below: | | | | |
| Ammonium chloride solution | No change. | JIS A 1509-10 : 2020 | | |
| Hydrochloric acid solution | No change. | | | |
| Citric acid solution | No change. | 3 A 1309-10 . 2020 | | |
| Potassium hydroxide solution | No change. | | | |
| Sodium hypochlorite solution | n hypochlorite solution No change. | | | |

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: ± 2.0 mm (143 ~ 147 mm)

May have small pinholes on surface due to its characteristic of pigments.

Clean with neutral detergent.

5mm joint is recommended.

